



ATAS INTERNATIONAL, INC.

SPECIFICATION DATA SHEET

1. PRODUCT NAME

VERSA-LOK PANEL
VSL123, VSL126, VSL163, VSL166

2. MANUFACTURER

ATAS INTERNATIONAL, INC.

website: www.atas.com

email: info@atas.com

Corporate Headquarters:

Allentown, PA 18106

Phone: (610) 395-8445

Fax: (610) 395-9342

Western Facility:

Mesa, AZ 85204

Phone: (480) 558-7210

Fax: (480) 558-7217

Southern Facility:

Maryville, TN 37801

Phone: (800) 468-1441

3. PRODUCT DESCRIPTION

Basic Uses:

Versa-Lok is a modular wall panel with a classic rectangular design. This versatile panel is available in various sizes to satisfy mix-and-match designs. The system utilizes concealed clips and fasteners.

Composition & Materials:

Standard Offerings: Versa-Lok panels are produced from .032 and .040 Aluminum.

Sizes:

Versa-Lok panels are available in standard sizes with a horizontal coverage of 36" or 60" and a vertical coverage of 12" or 16". Inquire for special panel sizes.

Colors & Finishes:

A choice of 30 colors is available in a KYNAR[®] 500 PVDF or HYLAR[®] 5000 PVDF finish.

(Request color chart or chips). An anodized finish is available in clear or dark bronze.

Texture is smooth.

4. TECHNICAL DATA

KYNAR[®] 500 PVDF or HYLAR[®] 5000 PVDF based finishes tested by paint supplier for:

Dry Film Thickness: ASTM D 1005,

ASTM D 1400, ASTM D 4138 or ASTM D 5796

Specular Gloss: ASTM D 523

Pencil Hardness: ASTM D 3363

T-Bend Flexibility: ASTM D 4145

Mandrel Bend Flexibility: ASTM D 522

Impact Resistance: ASTM D 2794

Adhesion: ASTM D 3359

Water Immersion Resistance: ASTM D 870

Abrasion Resistance: ASTM D 968

Acid Resistance: ASTM D 1308

Acid Rain Resistance (Kesternich):

ASTM G 87 or DIN 50018

Salt Spray: ASTM B 117

Cyclic Salt Spray: ASTM D 5894 and

ASTM D 5487

Humidity Resistance: ASTM D 2247

Accelerated Weathering: ASTM D 822 and

ASTM G 155, ASTM G 151 or ASTM G 153

Color Retention, Florida Exposure:

ASTM D 2244

Chalking Resistance: ASTM D 4214

Cleveland Condensing Cabinet:

ASTM D 4585

Cure Test, MEK Resistance: ASTM D 5402

Alkali Resistance, Sodium Hydroxide:

ASTM D 1308, Procedure 7.2

Flame Spread Rating: ASTM E 84

Organic coatings meet requirements of

AAMA 2605 when applied to aluminum.

Panel testing/ratings:

Aluminum: ASTM B 209

Coil Coating: ASTM A 755

Field Tested and Approved.

5. INSTALLATION

Versa-Lok panels have hems on all four sides. Panels are staggered and are installed from right to left using clips to secure the panel at the top and left edge as work progresses from the bottom of the wall to the top. Panels must be installed over a solid substrate covered with the appropriate water and air barrier system underlayment. Installation details or hands-on training via seminars are available through ATAS. Visit www.atas.com for more information.

6. AVAILABILITY & COST

Availability:

Versa-Lok panels are available through ATAS product distributors. A complete line of related components and trim accessories is available to complete the system. In addition, a complete line of rainware and perimeter roof edge trims can be supplied by ATAS to complement the application. Flat sheet and/or coil stock is available in matching color for fabrication of related components by the installing contractor.

Cost:

Contact ATAS product distributors for current pricing.

7. WARRANTY

The fluoropolymer, KYNAR 500[®] PVDF or HYLAR 5000[®] PVDF finish carries a thirty (30) year limited warranty against chalking and fading.

8. MAINTENANCE

Versa-Lok panels are virtually maintenance free. Surface residue may be easily removed by conventional cleaning methods. For painted products, minor scratches may be touched up with a matching paint, available from the manufacturer.

9. TECHNICAL SERVICES

Complete technical information and literature are available at www.atas.com. ATAS will assist with design ideas and shop drawings.

10. FILING SYSTEM

• www.atas.com

• Additional product information is available from the manufacturer upon request.

