

Standard Siliconized Polyester Roof and Wall Colors *In-stock, Standard Gloss*

Standard Polyester *Interior Only*



REGAL WHITE II
SR:0.61 E:0.88 SRI: 73



LIGHT STONE
SR:0.50 E:0.86 SRI: 57



GRAY STONE
SR:0.41 E:0.86 SRI: 45



REGAL WHITE I

Standard Fluoropon PVDF Wall and Roof Colors *In-stock, Low Gloss (wall applications), In-stock, Standard Gloss (roof applications)*



REGAL WHITE III
Low gloss: SR:0.66 E:0.87 SRI: 80
Std gloss: SR:0.68 E:0.86 SRI: 82



ALMOND
Low gloss: SR:0.62 E:0.87 SRI: 74
Std gloss: SR:0.60 E:0.84 SRI: 70



SANDSTONE
Low gloss: SR:0.59 E:0.87 SRI: 70
Std gloss: SR:0.54 E:0.86 SRI: 63



ASH GRAY
Low gloss: SR:0.48 E:0.87 SRI: 55
Std gloss: SR:0.39 E:0.84 SRI: 41



PATINA GREEN
Low gloss: SR:0.38 E:0.87 SRI: 41
Std gloss: SR:0.46 E:0.85 SRI: 51



SURREY BEIGE
Low gloss: SR:0.48 E:0.87 SRI: 55



ROMAN BLUE
Low gloss: SR:0.26 E:0.87 SRI: 25

Premium Metallics *Special Colors, Not in-stock, Additional Costs Will Apply*



TEXAS SILVER
SR:0.58 E:0.78 SRI: 66



LEADCOAT
SR:0.37 E:0.82 SRI: 38



WEATHERED GALVALUME
SR:0.30 E:0.79 SRI: 27



CHAMPAGNE
SR:0.38 E:0.80 SRI: 38




COPPER PENNY
SR:0.49 E:0.85 SRI: 55

Notes:


The colors above are representative and may vary slightly from actual colors. Prior to making final selections, please request actual color chip samples. All information is subject to change without notice.

Available Coating Products


Fluoropon Premiere



Fluoropon Classic® II
Mica Sparkle




Fluoropon®, WeatherX® & Dynapon®




Fluoropon Classic®


Metallic Sparkle



Flurothane® II




Flurothane® IV



Valshield®

Thick Film Plastisol



Notes:

Kynar 500® is a registered trademark of Arkema, Inc.

Hylar 5000® is a registered trademark of Solvay Solexis.

All coatings have a min/max thickness, average thickness is shown.